# PERMOHONAN PERSETUJUAN MATERIAL

Aplikasi Consol Floor 351 Ecocrete

| | | |
|---|---|---|
| **Nama Proyek** | : | Epoxy Flooring Area Shelter (Outdoor) PT. Mustika Lastari Jaya di Lanud Madiun |
| **Nomor SPK** | : | 009/PO/MLJ/I/2026 |
| **Lokasi Pekerjaan** | : | Area Shelter Lanud Madiun |
| **Item Pekerjaan** | : | Aplikasi Consol Floor 351 Ecocrete |
| **Tanggal Pengajuan** | : | 23 Juli 2026 |
| **Diajukan Oleh** | : | Andi Ahmad Raga |

## 1. MATERIAL YANG DIAJUKAN

*1.1.*

| | | | |
|---|---|---|---|
| **Nama Produk** | : | CONSOL PRIMER HYBRID EPOXY | |
| **Packaging** | : | 5.4 kg/set | |
| **Keterangan** | : | Consol Primer Hybrid berfungsi sebagai primer untuk memperkuat bonding beton dengan material Consol Floor 351 Ecocrete | |

*1.2.*

| | | | |
|---|---|---|---|
| **Nama Produk** | : | CONSOL FLOOR 351 ECOCRETE | |
| **Packaging** | : | 53.1 kg/set | |
| **Keterangan** | : | Sebagai material heavy duty epoxy water based untuk pekerjaan floor topping dan perbaikan lantai beton yang memiliki ketahanan terhadap abrasi, benturan, dan bahan kimia, serta memiliki daya rekat yang sangat baik pada substrat beton kering maupun lembap. | |

*1.3.*

| | | |
|---|---|---|
| **Nama Produk** | : SIDAFOS 480 SL | |
| **Packaging** | : 1 liter/pack | |
| **Keterangan** | : Membasmi gulma yang sudah tumbuh (purna tumbuh) di sekitar dan pada celah joint beton secara sistemik hingga ke akar | |

*1.4.*

| | | |
|---|---|---|
| **Nama Produk** | : GOAL 240 EC | |
| **Packaging** | : 50 ml/pack | |
| **Keterangan** | : Mencegah pertumbuhan/perkecambahan biji gulma baru pada joint beton, sehingga area tetap bersih setelah treatment Sidafos (residual hingga 30-40 hari). | |

*1.5.*

| | | |
|---|---|---|
| **Nama Produk** | : BACKROD | |
| **Packaging** | : 500 m/roll | |
| **Keterangan** | : Backrod berfungsi sebagai material pengisi (joint filter) yang dipasang di dasar joint sebelum sealent diaplikasikan. | |

*1.6.*

| | | |
|---|---|---|
| **Nama Produk** | : BOSTIK P795 SEAL'N'FLEX FC PREMIUM | |
| **Packaging** | : 600 ml/ssg | |
| **Keterangan** | : Sealant polyurethane 1 komponen yang juga berfungsi sebagai perekat. Produk ini memiliki elastisitas tinggi, cepat kering, tidak menyusut, bebas gelembung saat curing, serta memiliki daya rekat yang sangat baik pada berbagai permukaan, termasuk permukaan lembap. | |

## 2. LEMBAR PERSETUJUAN

| Diajukan Oleh | Diperiksa Oleh | Disetujui Oleh |
|---|---|---|
| (Andi Ahmad Raga) | (_____) | (_____) |
| Tanggal: _____ | Tanggal: _____ | Tanggal: _____ |

# CONSOL PRIMER HYBRID EPOXY

Water Based Epoxy Primer

## DESCRIPTION

**CONSOL PRIMER HYBRID EPOXY** is two components, water based epoxy and solvent free. The system is formulated to bind to damp, dry, and green concrete.

## RECOMMENDED FOR

**CONSOL PRIMER HYBRID EPOXY** can be used as primer and adhesion promoter for epoxy and polyurethane floor on:

- Concrete floors
- Cementitious Mortar Screed
- Epoxy Cement Floor
- Epoxy Mortar Floor
- Epoxy Concrete Floor

## BENEFITS

**CONSOL PRIMER HYBRID EPOXY** provides the following beneficial properties such as:

- Low viscosity
- Solvent free
- Low odour
- Excellent bonding strength
- Water based
- Excellent adhesion to dry, damp, green concrete

## COVERAGE

Material consumption approx. 0.15 - 0.3 kg/m$^2$ depends on substrate conditions

## PRODUCT DATA

### Form

Liquid

### Colour

Part A : Milky white, liquid
Part B : Green to brown, liquid

### Density

Part A : 1.05 kg/L
Part B : 1.05 kg/L

### Bond Strength

1.5 N/mm$^2$ (Failure on concrete)

### Pot Life (30$^0$C)

Approx. 20 minutes

### Storage

Dry, cool, shaded place

### Shelf Life

1 years if stored in unopened original container

### Packaging

Part A : 2.1 kg
Part B : 3.3 kg

## INSTRUCTION FOR USE

### Substrate Condition

Surfaces must be structurally sound, clean, and free from loose particles, oil, grease, and all other contaminants. The compressive strength of the substrates shall not be less than 20 N/mm$^2$ and the bond strength of the substrate must be at least 1.5 N/mm$^2$.

### Surface Preparation

Remove oil, grease, and wax contaminants by scrubbing with industrial grade detergent or degreasing compounds followed by mechanical cleaning. Cement laitance, loose particles, mould release agents, curing membrane and other contaminants must be removed from the surface by shot blasting, scarifying or grit-blasting followed by vacuum cleaning.

### Mixing

As Primer
Mixing use a low speed (300 rpm) electric mixer, mix part A&B for at least 3 minutes until the mix is uniform.

**Mixing Ratio:**
General primer : **A : B = 2.1 : 3.3**

**Head Office**
Ruko Wadungasri Permai Blok B 8
Jl. Wadungasri 46-48 Waru-Sidoarjo
Telp. 031-8661122 - Fax. 031-99004958

**Branch Office**
Kawasan Industri Lippo Cikarang II
Delta Silicon 5, Jl. Daru III, Blok G5, No. 53
Cicau, Bekasi, Jawa Barat 17530
Telp. 021-89914905

**Factory**
Kompleks Industri dan Pergudangan
Golden Blok B16-17
Jl. Industri II Tambak Sawah, Waru-Sidoarjo

## APPLICATION

As Primer

Apply **CONSOL PRIMER HYBRID EPOXY** by squeegee or brush on to the prepared surface.
If the surface has moisture barrier, allow the moisture barrier to dry before apply **CONSOL PRIMER HYBRID EPOXY**.
Curing:
At 30 $^{0}$C, foot traffic access in 6 hours, fully cured in 48 hours.

## PRECAUTIONS

- **CONSOL PRIMER HYBRID EPOXY** contain certain chemicals which can cause skin irritation if exposed and respiratory reaction if inhaled.
- Keep away from open light, including welding.
- Avoid contact with skin and eyes.
- If skin contact occurs, wash skin thoroughly.
- Wear protective glove and eye protection during work.
- If in eyes, hold eyes open, flood with warm water and seek medical attention without delay.
- Not classified as finishing material, and slightly color difference on result may occurred.

# CONSOL FLOOR 351 ECOCRETE

## A Heavy Duty, Epoxy Water Based

## DESCRIPTION

**CONSOL FLOOR 351 ECOCRETE** is a heavy duty, 4 components, solvent free, odorless, moisture tolerant epoxy water based.

## RECOMMENDED FOR

**CONSOL FLOOR 351 ECOCRETE** is mainly used for the following applications:

- Floor topping on damp and dry substrate
- Repair and maintenance of monolithic concrete floor
- Chemical and pharmaceutical industry
- Food and beverage industry
- Automotive and aircraft servicing facilities
- Production and packaging areas
- Commercial and industrial kitchens

## BENEFITS

**CONSOL FLOOR 351 ECOCRETE** bring some benefits such are:

- Impact and abrasion resistant
- Chemical resistant
- Waterbased, solvent free and odourless
- Excellent adhesion to dry, damp, green or saturated surface dry concrete
- Vapour permeable
- Can be applied to fresh and damp concrete
- Resistance to thermal shock
- Adaptable thickness

## PRODUCT DATA

### Form

Part A : Liquid
Part B : Liquid
Part C : Powder
Part D : Mixed aggregate

### Appearance

White, cream, green, grey, light grey, stone grey

### Packaging

Part A : 4.1 kg
Part B : 5.3 kg
Part C : 21.2 kg
Part D : 22.5 kg
Part ABCD : 53.1 kg/set

### Storage

Dry, shaded place. Protect from direct sunlight and frost.

### Shelf Life

12 months from the date of production, if stored properly in original, unopened and undamaged sealed container in dry condition between 10-32 °C. Protect from direct sunlight.

### Limitation

- The "matte" of the finish can vary with temperature and the absorbency of the substrate.
- For exact color matching, ensure the **CONSOL FLOOR 351 ECOCRETE** in each area is applied from the same control batch number.

## TECHNICAL DATA

### Coverage

Primer:

- CONSOL PRIMER HYBRID EPOXY : ± 0.15 kg/m$^2$ (depend on surface condition); or
- CONSOL FLOOR 161/162 : ± 0.1 - 0.2 kg/m$^2$ (depend on surface condition)

Top Coat:

- **CONSOL FLOOR 351 ECOCRETE**: approx.11 kg/m$^2$ for ± 5 mm layer thickness

### Density

~2.2 kg/L

### Pot Life (30 °C)

~15 Minutes

**Head Office**
Ruko Wadungasri Permai Blok B 8
Jl. Wadungasri 46-48 Waru-Sidoarjo
Telp. 031-8661122 - Fax. 031-99004958

**Branch Office**
Kawasan Industri Lippo Cikarang II
Delta Silicon 5, Jl. Daru III, Blok G5, No. 53
Cicau, Bekasi, Jawa Barat 17530
Telp. 021-89914905

**Factory**
Kompleks Industri dan Pergudangan
Golden Blok B16-17
Jl. Industri II Tambak Sawah, Waru-Sidoarjo

### Curing Time
Foot traffic : 1 day
Light traffic : 2 days

### Full Cure
5 Days

### Hardness
Shore D hardness > 80

### Compressive Strength
~20 N/mm$^2$ after 28 days

### Flexural Strength
~7.5 N/mm$^2$ after 28 days

## INSTRUCTION FOR USE

### Substrate Preparation
Surfaces must be structurally sound, clean, and free from loose particles, oil, grease, and all other contaminants. The compressive strength of the substrates shall not be less than 20 N/mm$^2$, and the bond strength of the substrate must be least 1.5 N/mm$^2$.

### Surface Preparation
Remove oil, grease and wax contaminants by scrubbing with industrial grade detergent or decreasing compounds followed by mechanical cleaning. Cement laitance, loose particles, mold release agents, curing membrane and other contaminants must be removed from the surface by shot-blasting, scarifying or grit-blasting followed by vacuum cleaning.

### Mixing
Add part A, to a clean mixing drum. Add part B to the drum and mix for 10 second until uniform using helical spinner. Add the pigmented part C (powder) and part D (mixed aggregate) and stir for ±3 minutes to achieve a fully homogenous consistent mortar. Scrap out residue of previous mix from the sides of the drum and discard before the next pack, stir and mix well both content well with high-speed mixer (750 rpm).

### Application
Apply **CONSOL FLOOR 351 ECOCRETE** within its pot life. Spread the composite matrix to thickness 5-10 mm and consolidate with steel trowel to the correct depth as desired. Immediately release air by spike roller.

### Cleaning
Use soap and water. Hardened material may have to be mechanically removed.

## HEALTH & SAFETY
Some of the component of this product may be hazardous during mixing and application. Always use with suitable protective gears. Close container tightly after use. Keep out of reach of children.
For further information, refer to the product Material Safety Data Sheet, available upon request.

# P795

## SEAL'N'FLEX FC PREMIUM

### ADVANCED DURABLE FLEXIBLE BUILDING AND CONSTRUCTION SEALANT

## TECHNICAL DATA SHEET

### BENEFITS

- 3-in-1 sealant (vertical & horizontal) & adhesive
- Bubble free curing
- Excellent toolability
- Suitable for wider joints (up to 50mm)
- Permanently elastic
- High mechanical resistance
- No shrinkage
- Adheres perfectly without primer on most, even damp, surfaces

### PRODUCT DESCRIPTION

**Bostik P795 SEAL'N'FLEX FC PREMIUM** is a *New Generation* one component user friendly low MDI fast curing high performance and durable polyurethane sealant. **Bostik P795 SEAL'N'FLEX FC PREMIUM** will **not form bubbles** during its curing process. It has total movement capability of 100% (±50%) for continuous expansion and compression cycles.

### APPLICATIONS

**Bostik P795 SEAL'N'FLEX FC PREMIUM** is specifically developed as a universal sealant for sealing construction & expansion joints, joints in pedestrian walkways and suitable for roofing applications, complies NFP 85-610. **Bostik P795 SEAL'N'FLEX FC PREMIUM** is also bonding adhesive for light fixtures and accessories.

### DIRECTIONS OF USE

A joint with the correct dimensions is able to absorb movements between building materials. The joint depth should always be in the correct relationship of the joint width. A general rule is the ratio of joint depth to the width of the joint with a joint width up to 10mm is 1:1, with a minimum of 5mm in width and depth. For joints wider than 10mm, the depth is the width divided by 3 plus 6mm.

### LIMITATIONS

- Not suitable for PE, PP, PC, PMMA, PTFE, soft plastics, neoprene and bituminous substrates
- Not suitable in combination with chlorides (pools)

### TECHNICAL DATA

| | | |
|---|---|---|
| 100% modulus | ASTM D 412, BTM-U023 | >1.0 N/mm² |
| Application temperature | | +5°C to + 40°C |
| Base | | New Generation PU |
| Curing time | @ +23°C/50% RH | 3 mm/24 hours |
| Density | ISO 1183-1 | 1.30 g/ml |
| Elongation at break | ASTM D 412, BTM-U023 | > 900% |
| Flow | ISO 7390 | 0 mm |
| Movement Capability | ASTM C 719 | ±50% |
| Shore A hardness | BTM-P003, ASTM C 661-15 | 37 - 44 |
| Shrinkage | ISO 10563 | < 10% |
| Skin formation | ASTM C 676 | 50 min. |
| Temperature resistance | | -30°C to +80°C |
| Tensile strength | ASTM D 412, BTM-U023 | 1.69 N/mm² |

*These values are typical properties and may vary +/-3%*

### SURFACE PREPARATIONS AND FINISHING

Application temperature + 5°C to + 40°C (applies to environment and substrates). All substrates must be solid, clean, dry, and free of grease and dust. Clean substrates with Bostik Cleaner. **Bostik P795 SEAL'N'FLEX FC PREMIUM** adheres perfectly without the use of a primer to most porous & non-porous substrates. In order to achieve maximum adhesion especially to concrete in which dust can't be avoided, Bostik Primer (or Bostik N49) is highly

recommended. Always test adhesion prior to application. Use Bostik Finisher to smooth the joint.

## PAINTABILITY

**Bostik P795 SEAL'N'FLEX FC PREMIUM** is paintable with water based and most 2-component paints. Synthetic paints can dry slower. We recommend testing compatibility with paint prior to application.

## CLEANING

Uncured material and tools can be cleaned by using Bostik Cleaner. Cured material can only be mechanically removed. Hands can be cleaned with Bostik Wipes.

## COLOUR(S)

- White
- Off-white
- Light-grey
- Mid-grey
- Dark-grey
- Black

## PACKAGING

- 300 ml Cartridge, 12 per box
- 600 ml Sausages, 12 per box

*For product specifications, please refer to the Online Product Detail Page*

## SHELF LIFE

In unopened original packaging between + 5°C and + 25°C, shelf life is up to 15 months from production date, stored in a dry place.

## HEALTH & SAFETY

Product Safety Data Sheet must be read and understood before use. These are available on request and via the websites.

## CERTIFICATIONS

- F-EXT-INT-CC 25HM
- PW-EXT-INT-CC 25HM
- SNJF 25E
- ASTM C-920 as Type S, Grade NS, Class 50, use T, G, A, M & O as external & traffic joint sealant
- ISEGA (direct food contact)
- A+ French VOC Regulation

**The information and recommendations relating to the application and end-use of the product are given in good faith and based on tests which we believe to be reliable. Differing materials, substrates, environments, site conditions, and product storage, handling and application may affect results. However, no warranty in respect of merchantability or fitness for a particular purpose, nor any liability arising out of any legal relationship, whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advise offered. No guarantee of their accuracy can be made because of the great range of field conditions and variation encountered in raw materials, manufacturing equipment and methods. Thus, the products are sold with limited warranty only, and on condition that purchasers will make their own tests to determine the suitability of the product for their particular purposes. Under no circumstances will Bostik be liable to anyone except for replacement of the products or refund of the purchase price.**

**Bostik S.A**
420 rue d'Estienne d'Orves, 92700, Colombes, France
Tel.: +31 (0)162 491 000
www.bostik.com

**BOSTIK SMART SUPPORT**

**Smart help digital**
**Bostik.com/**

**Smart help**
**+31 (0)162 491 000**